CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

An ISO 9001:2008 Certified Company

NABL - Accredited Laboratory as per ISO / IEC-17025 : 2005

JAS-ANZ BSCIC ISO 9001 REGISTERED

Job No.: CTCE/BBMP/KRIDL/W.No.13/BM/Shape.T/2018-19 04.04.2018

TEST REPORT ON FLAKINESS INDEX & ELONGATION INDEX OF COARSE AGGREGATES

* Customer	:	**Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP Bangalore.
* Agency	:	**Technical Manager (West),** KRIDL, Bangalore.
* Name of Work	:	Improvements of Asphalting at BHEL Mini Colony surrounding area in Mallasandra Ward No.13, Shettyhalli, Sub Division, BBMP, Bangalore.
* Reference	:	BBMP/EE/DD/WO/222/2017-18 Dated:07.02.2018
* Sample ID	:	Hot Mix Plant, Bangalore
Technical Reference	:	IS : 2386(Part -1)-1963 (RA-2011)
* Type of Mix	:	Bituminous Macadam
Date of Testing	:	04.04.2018



Sl.No.	Description	Result
1	Flakiness Index	11.60%
2	Elongation Index	13.25%
3	Combined Flakiness & Elongation Index	24.85%

*Information is furnished by the Customer/Representative.

Civil-Tech Consultants & Engineers Bangalore

Comments:

→ Maximum allowable Flakiness & Elongation Index for Bituminous Macadam is 30%

Note:

⇒The report shall not be reproduced, except in full, without the written approval of the laboratory.

⇒The results indicated above are based on the tests carried out on the samples received in the

⇒Any Query regarding the report must be reported within 30 days from the date of testing.

****

Civil-tech Consultants & Engineers
#23/14, 7th Cross 3rd Stage 4th Block,
Shakthi Ganapathinagar,
Basaveshwaranagar, Bangalore-560 079.

Scanned by CamScanner

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

An ISO 9001:2008 Certified Company

NABL - Accredited Laboratory as per ISO / IEC-17025 : 2005

JAS-ANZ BSCIC ISO 9001 REGISTERED

Job No: CTCE/BBMP/KRIDL/W.No.13/BM/Stripping/2018-19 06.04.2018

TEST REPORT ON STRIPPING VALUE OF ROAD AGGREGATE (STATIC IMMERSION TEST)

* Customer	:	**Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP Bangalore.
* Agency	:	**Technical Manager (West),** KRIDL, Bangalore.
* Name of work	:	Improvements of Asphalting at BHEL Mini Colony surrounding area in Mallasandra Ward No.13, Shettyhalli, Sub Division, BBMP, Bangalore.
* Reference	:	BBMP/EE/DD/WO/222/2017-18 Dated:07.02.2018
Technical reference	:	IS: 6241
* Type of Mix	:	Bituminous Macadam
Date of Testing	:	06.04.2018

Type of binder : 60/70
Percentage of binder used : 5.0% by wt.
Total weight of aggregate : 200 g
Total weight of binder : 10.0 g
Temperature of water-bath : 40° C

Observation Number	Stripping, Percentage	Average, Percentage	Average Retained Coating, %
1	3.3	3.40	96.60
2	3.4		
3	3.5		

*Information is furnished by the Customer/Representative.

Comments:

→ Minimum allowable Aggregate retained coating for Bituminous Macadam is 95%

Civil-tech Consultants & Engineers Bangalore

Note:

→ The report shall not be reproduced, except in full, without the written approval of the laboratory.

→ The results indicated above are based on the tests carried out on the samples received in the laboratory.

→ Any Query regarding the report must be reported within 30 days from the date of testing.

****

Civil-tech Consultants & Engineers
#23/14, 7th Cross 3rd Stage 4th Block,
Shakthi Ganapathinagar,
Basaveshwaranagar, Bangalore-560 079.

Scanned by CamScanner

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

An ISO 9001:2008 Certified Company

NABL - Accredited Laboratory as per ISO / IEC-17025 : 2005

JAS-ANZ BSCIC ISO 9001 REGISTERED

Job No: CTCE/BBMP/KRIDL/W.No.13/BM/Sp_Wa/2018-19 06.04.2018

TEST REEPORT ON SPECIFIC GRAVITY AND WATER ABSORPTION

* Customer	:	**Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP Bangalore.
* Agency	:	**Technical Manager (West),** KRIDL, Bangalore.
* Name of Work	:	Improvements of Asphalting at BHEL Mini Colony surrounding area in Mallasandra Ward No.13, Shettyhalli, Sub Division, BBMP, Bangalore.
* Reference	:	BBMP/EE/DD/WO/222/2017-18 Dated:07.02.2018
Technical reference	:	IS : 2386(Part -3)-1963 (RA-2011)
* Type of Mix	:	Bituminous Macadam
Date of Testing	:	06.04.2018

Sl. No.	Details	Notation	Test Number			Mean Value
			Test 1	Test 2	Test 2	
1	Weight of aggregate suspended in water with the basket	W_1 g	2010	2012	2014	
2	Weight of basket suspended in water	W_2 g	750	750	750	
3	Weight of saturated aggregate in water	$(W_1 - W_2) = W_s$ g	1260	1262	1264	
4	Weight of saturated surface dry aggregate in air	W_3 g	2024	2027	2029	
5	Weight of water equal to the volume of the aggregate	$(W_3 - W_S)$ g	764	765	765	
6	Weight of oven dried aggregate	W_4 g	2014	2016	2018	
7	Specific Gravity	$W_4/(W_3-W_S)$	2.636	2.635	2.638	2.637
8	Apparent Specific gravity	$W_4/(W_4-W_S)$	2.671	2.674	2.676	2.674
9	Water Absorption	$((W_3-W_4)*100)/W_4$	0.50%	0.55%	0.55%	0.52%

*Information is furnished by the Customer/Representative.

Comments:

⇒ Maximum allowable Aggregate Water absorption value for Bituminous Macadam is 2.0%

Note:

⇒The report shall not be reproduced, except in full, without the written approval of the laboratory.

⇒The results indicated above are based on the tests carried out on the samples received in the laboratory.

⇒Any Query regarding the report must be reported within 30 days from the date of testing.

****

Civil-tech Consultants & Engineers
#23/14, 7th Cross 3rd Stage 4th Block,
Shakthi Ganapathinagar,
Basaveshwaranagar, Bangalore-560 079.

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

Scanned by CamScanner

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

An ISO 9001:2008 Certified Company

NABL - Accredited Laboratory as per ISO / IEC-17025 : 2005

JAS-ANZ BSCIC ISO 9001 REGISTERED

Job No.: CTCE/BBMP/KRIDL/W.No.13/BM/Bitumen/2018-19 06.04.2018

TEST REPORT ON BITUMEN CONTENT DETERMINATION OF BITUMINOUS MACADAM MIX

* Customer	:	**Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP Bangalore.
* Agency	:	**Technical Manager (West),** KRIDL, Bangalore.
* Name of work	:	Improvements of Asphalting at BHEL Mini Colony surrounding area in Mallasandra Ward No.13, Shettyhalli, Sub Division, BBMP, Bangalore.
* Reference	:	BBMP/EE/DD/WO/222/2017-18 Dated:07.02.2018
* Sample ID	:	Road at BHEL Mini Colony, Mallasandra Ward No.13,
Technical Reference	:	IRC:SP:11-1984
Date of Testing	:	06.04.2018

BITUMEN CONTENT DETERMINATION

Description	Trail 1	Trail 2
1. Weight of Mixture before Test, g	500	500
2. Weight of Mixture after Test, g	482.5	481.5
3. Weight of Asphalt and Mineral matter Extracted, g		-
4. Weight of Mineral Matter, g.	-	-
5. Weight of Ash, g		
6. Weight of Bitumen Extracted, g. (corrected)	17.5	18.50
7. Bitumen content in %	3.50	3.70
8. Average	3.60	

AC-13

*Information is furnished by the Customer/Representative.

Civil-Tech Consultants & Engineers Bangalore

Note:

- This test report should not be reproduced except in full, without written approval of the laboratory
- The results indicated above are based on the tests carried out on the samples collected by the laboratory
- Any Query regarding the report must be reported within 30 days from date of testing.

****

Civil-tech Consultants & Engineers
#23/14, 7th Cross 3rd Stage 4th Block,
Shakthi Ganapathinagar,
Basaveshwaranagar, Bangalore-560 079.

Scanned by CamScanner

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory
An ISO 9001:2008 Certified Company
NABL - Accredited Laboratory as per ISO / IEC-17025 : 2005

JAS-ANZ BSCIC ISO 9001 REGISTERED

Job No.: CTCE/BBMP/KRIDL/W.No.13/BM/Bitumen/2018-19 06.04.2018

TEST REPORT ON GRADATION OF BITUMINOUS MACADAM MIX

* Customer	:	**Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP Bangalore.
* Agency	:	**Technical Manager (West),** KRIDL, Bangalore.
* Name of work	:	Improvements of Asphalting at BHEL Mini Colony surrounding area in Mallasandra Ward No.13, Shettyhalli, Sub Division, BBMP, Bangalore.
* Reference	:	BBMP/EE/DD/WO/222/2017-18 Dated:07.02.2018
* Sample ID	:	Road at BHEL Mini Colony, Mallasandra Ward No.13,
Technical Reference	:	IS:2386 and IRC:SP:11-1984
Date of Testing	:	06.04.2018

GRADATION AFTER EXTRACTION

Sieve Size in mm	Trail 1				Specified Limits as per MORTH specification table 500-04 (Grading-2)
	Weight Retained, gm	% Retained	%Cummulative Retained	% Passing	
26.5	0	0	0.00	100	100
19	35.24	7.30	7.30	92.70	90-100
13.2	80.12	16.61	23.91	76.09	56-88
4.75	255	52.85	76.76	23.24	16-36
2.36	55.26	11.45	88.21	11.79	4-19
0.3	25.31	5.25	93.46	6.54	2-10
0.075	8.62	1.79	95.24	4.76	0-8

Sieve Size in mm	Trail 2				Specified Limits as per MORTH specification table 500-04 (Grading-2)
	Weight Retained, gm	% Retained	%Cummulative Retained	% Passing	
26.5	0	0	0.00	100	100
19	30.51	6.34	6.34	93.66	90-100
13.2	84.26	17.50	23.84	76.16	56-88
4.75	265	55.04	78.87	21.13	16-36
2.36	50.14	10.41	89.29	10.71	4-19
0.3	32.65	6.78	96.07	3.93	2-10
0.075	7.25	1.51	97.57	2.43	0-8

At-13

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ಮಹಾಲಕ್ಷ್ಮೀಪುರಂ ವಿಭಾಗ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎಂ. ಕೃಷ್ಣ ರಾಜೇಂದ್ರನಗರ, ಬೆಂಗಳೂರು

*Information is furnished by the Customer/Representative.

Note:

⇒The report shall not be reproduced, except in full, without the written approval of the laboratory.

⇒The results indicated above are based on the tests carried out on the samples received in the laboratory.

⇒Any Query regarding the report must be reported within 30 days from the date of testing.

****

Civil-tech Consultants & Engineers Bangalore

Civil-tech Consultants & Engineers
#23/14, 7th Cross 3rd Stage 4th Block,
Shakthi Ganapathinagar,
Basaveshwaranagar, Bangalore-560 079.

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

Scanned by CamScanner